

# Critical Guidance Protocol for HDPE Colored Bottles with Labels

Document number – HDPE-CG-03

Revision date – August 17, 2021

## Introduction – Scope, significance and use

This is a comprehensive laboratory scale evaluation, or protocol, that can be used to assess the compatibility of HDPE rigid container packaging innovations with reclamation systems sourcing post-consumer material.

HDPE rigid containers typically consist of natural homopolymer, natural copolymer, and colored copolymer bottles, jars, and jugs. This test is appropriate for HDPE colored bottle packaging innovations and components including printing, labels, and adhesives.

In APR Processing Practices and Test Protocols, the term “article” is used to mean the package submitted for testing (except in the special case where a resin pellet is tested and is referred to simply as “resin pellet”). The article incorporates the innovation or design feature which requires test data for an APR recyclability classification.

Data developed by an independent third-party laboratory following this protocol can be used in petitions for APR’s Critical Guidance Recognition. Petitions require data for an innovative article compared to a control.

In certain cases, before Critical Guidance Protocol test results can be submitted to APR for consideration of guidance recognition, all pre-requisite tests, including sortation potential protocols and degradable additives testing, must be passed and such evidence must be presented with any guidance applications. In addition, the Program Administrator may ask for additional exposure testing and performance testing as are pertinent to the innovation. To determine when pre-requisite testing is needed, please refer to the [APR HDPE Design® Guide text and tables](#) and the following test protocols and resources.

For products or innovations that employ metal decoration or which contain metal components:

- [APR RES-SORT-1 Metal Sorting Resource](#)
- [APR SORT-B-03 Metal Sortation Protocol](#)

For items less than 5 cm in 2 dimensions:

- [APR RES-SORT-3 Size Sortation Resource](#)
- [APR SORT-B-02 Size Sortation Protocol](#)
- [APR SORT-PR-01 Compression Practices](#)

For dark colors and label coverage (see definition in Design® Guide):

- [APR RES-SORT-2 NIR Sorting Resource](#)
- [APR SORT-B-01 NIR Sortation Protocol](#)
- [APR-SORT-B-04 Color Sortation Protocol](#)

For materials that might be employed or marketed as degradable additives for plastics and which might be expected to display time dependent behavior or change with environmental exposure where appearance or physical properties can change over time:

- [APR O-S-03 HDPE/PP Degradable Additives Test](#)

This list is not inclusive. The Critical Guidance Protocol is not appropriate for package constructions that are not in alignment with the APR Design® Guide for Plastics Recycling text in cases where additional conditions are specified in the relevant Design® Guide section.

**Disclaimer:** *This document has been prepared by the Association of Plastic Recyclers as a service to the plastic industry to promote the most efficient use of the nation's plastic recycling infrastructure and to enhance the quality and quantity of recycled postconsumer plastic. The information in this document is offered without warranty of any kind, either expressed or implied, including WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, which are expressly disclaimed. APR and its members accept no responsibility for any harm or damages arising from the use of or reliance upon this information by any party. Participation in the Recognition Program is purely voluntary and does not guarantee compliance with any U.S. law or regulation or that a package or plastic article incorporating the innovation is recyclable or will be recycled.*

*The results of testing using APR's Critical Guidance Test Protocols along with a Critical Guidance Technical Review are intended to qualify a company's innovation for APR's Critical Guidance Recognition only. The complete testing protocol process requires a review of the test results by a Technical Review Team convened by APR. If test results are not reviewed by an APR Technical Review Team, no APR recognition is possible. APR does not give permission for its name to be used to claim, or to imply in any way, that APR has recognized or approved the design feature or innovation that was tested when APR has not reviewed the test results*

*The APR's Critical Guidance Recognition does not convey any consideration by any other organization nor guarantee recognition by any other organization. APR does not share submitted data with any other organizations. Whether a company achieves APR recognition is solely dependent upon the results of an APR review of test data. If APR intellectual property is to be used as documentation or justification toward any other organization's evaluation or recognition, no claim of APR approval or recognition may be made under such circumstances without the express written permission of APR. When data are used by other organizations outside of APR's recognition programs, in the absence of a licensing agreement with such organizations, the APR does not give permission for its name to be used to claim, or to imply in any way, that APR has recognized or approved the design feature or innovation that was tested. APR does not recommend, advocate, or influence any other organization's decision making in this regard.*

*Although test data generated by a company is the property of that company and may be used for other purposes besides APR Critical Guidance Recognition, the test protocols are the property of APR and APR requires that they be used as written in their entirety. It should also be noted that partial test results that may under-report negative impacts from an innovation or design feature could misrepresent APR's intention or position and will be called out by APR when these incidents come to APR's attention.*

## Method Summary

This Critical Guidance protocol provides two pathways for testing HDPE resins and articles with flow diagrams found on pages 8 and 9 for articles that employ, printing, labels, and adhesives. Controls are comprised of similar articles made solely with a control PE resin without the innovation. Reference document [APR Polyolefin Standard Laboratory Processing Practices, O-P-00 through O-P-07](#) for complete details.

**Path 1** - Path 1 is utilized for complete HDPE packages in the form of bottles, jars and jugs that include the innovation being tested. A flow diagram for Path 1, on page 8 illustrates that these articles are separately processed through these steps:

- Granulation
  - Commercial Basic Wash and drying
  - Elutriation
  - Blends created from the processed materials. APR Critical Guidance protocols require blends of 50% control and 50% innovation to be compared with 100% control material. Optional blends can be used if desired by the investigator at 75% control and 25% innovation blend.
  - Blends dried, extruded and pelletized
  - Pellets subjected to testing and evaluation
1. Injection molding or compression molding of test bars for required ASTM tests of each blend (ESCR testing optional). Injection molding is recommended but compression molding may be used for low melt index polymers. In this case ASTM D4976 should be referenced.

**Path 2** - Path 2 is utilized for testing resins and resin blends that incorporate the innovation being tested but have not been converted into package form. A flow diagram for Path 2, on page 9 illustrates that these articles are separately processed through these steps:

- Control and test dry blends processed for a single melt history to represent the initial production.
  - Blends created from the processed materials. APR Critical Guidance protocols require blends of 50% control and 50% innovation to be compared with 100% control material. Optional blends can be used if desired by the investigator at 75% control and 25% innovation blend.
  - Blends dried, extruded and pelletized
  - Pellets subjected to testing and evaluation
2. Injection molding of test bars for required ASTM tests of each blend (ESCR testing optional). Injection molding is recommended but compression molding may be used for low melt index polymers. In this case ASTM D4976 should be referenced.

## Reference Documents

The following documents are referenced in this Critical Guidance Protocol:

[APR Polyolefin Standard Laboratory Processing Practices](#), O-P-01 through O-P-07

APR Screening Test Methods:

[Polyolefin Packaging Article Sink or Float Evaluation](#), O-S-01

ASTM Pellet Test Methods:

ASTM D3418 Transition Temperatures and Enthalpies of Fusion and Crystallization of Polymers by Differential Scanning Calorimetry

ASTM D1238 Melt Flow Rates of Thermoplastics by Extrusion Plastometer

ASTM D792 Density and Specific Gravity (Relative Density) of Plastics by Displacement

ASTM D1505 Density of Plastics by the Density-Gradient Technique

ASTM D5630 Ash Content in Plastics

ASTM D6980 Determination of Moisture in Plastics by Loss in Weight

ASTM D7399 Determination of the Amount of Polypropylene in Polypropylene/Low Density Polyethylene Mixtures Using Infrared Spectrophotometry

ASTM Part Test Methods:

ASTM D638 Tensile Properties of Plastics

ASTM D256 Determining the Izod Pendulum Impact Resistance of Plastics

ASTM D790 Flexural Properties of Unreinforced and Reinforced Plastics and Electrical Insulating Material

ASTM D4976 Polyethylene Plastics Molding and Extrusion Materials

Optional ASTM Test Methods:

ASTM D1693 Environmental Stress-Cracking of Ethylene Plastics

## Method Steps for Extrusion Blends and Evaluation

**Safety Statement:** *APR Test and Practice documents do NOT CLAIM TO ADDRESS ALL OF THE SAFETY ISSUES, IF ANY, ASSOCIATED WITH THEIR USE. These Tests and Practices may require the use of electrically powered equipment, heated equipment and molten polymers, rotating motors and drive assemblies, hydraulic powered equipment, high pressure air, and laboratory chemicals. IT IS THE RESPONSIBILITY OF THE USER TO ESTABLISH AND FOLLOW APPROPRIATE SAFETY AND HEALTH PROCEDURES WHEN UNDERTAKING THESE TESTS AND PRACTICES THAT COMPLY WITH APPLICABLE FEDERAL, STATE AND LOCAL REGULATORY REQUIREMENTS. APR and its members accept no responsibility for any harm or damages arising from the use of or reliance of these Tests and Practice documents by any party.*

### Path 1 Method Steps

The following steps are taken to prepare samples for evaluation; these steps are illustrated in the flow diagram labeled Path 1, and details of each step are presented in the [APR Polyolefin Standard Laboratory Processing Practices, O-P-01 through O-P-07](#) (included in document O-P-00). The amount of material will depend upon the equipment and scale used in each laboratory.

3. Obtain control and test article to use in the evaluation for Path 1. For a list of acceptable control resins, refer to Practice O-P-01.
4. For each of the test and control articles for Path 1, separately:
  - a. Granulate articles
  - b. Sink-float the control and test articles per the Screening Test O-S-01
  - c. Commercial Basic Wash and drying
  - d. Elutriation of granulated material
5. Prepare the following required blends:
  - a. 100% processed control - Sample A
  - b. 50/50 processed control and innovation – Sample B
  - c. Any optional blends chosen by the investigator, for example: 75/25 processed control and innovation – Sample C
6. Extrude blends and melt filter to create the samples: A pellets, B pellets and C pellets.
  - a. Extruded pellets to be evaluated for DSC, melt flow, density, ash content, moisture content, and FTIR.
7. Injection Mold test parts for required ASTM tests of each blend (ESCR testing optional). Injection molding is recommended but compression molding may be used for low melt index polymers. In this case ASTM D4976 should be referenced.

## Path 2 Method Steps

If the form submitted for testing is resin instead of containers, Path 1 method steps 1 and 2 are unnecessary. Steps 3, 4, and 5 for resin samples are illustrated in the flow diagram labeled Path 2.

Details of each step are presented in the [APR Polyolefin Standard Laboratory Processing Practices](#), O-P-01 through O-P-07 (included in document O-P-00).

The amount of material will depend upon the equipment and scale used in each laboratory.

### Measurements, Report and Guidance Values

#### Path 1 - Incoming Flake Analysis

Property	Method	APR Guidance Preferred values	Additional Guidance
<u>Required values</u>			
Sink-float	O-S-01	100% Floatability for Olefin material	Any non-PO labels, closures, layers, attachments, or other materials must either sink in water and be removed or must be compatible with PE. It is unacceptable for a non-PE material to stick to or otherwise not separate from the PE substrate and cause the PE to sink, resulting in yield loss, or stay with the PE and contaminate the PE.

#### Path 2 - 1<sup>st</sup> Melt History Extruded Pellet

Property	Method	APR Guidance Preferred values	Additional Guidance
<u>Optional Values</u>			
Screen Pack Pressure Build	Practice O-P-06	Record and Report	No guidance; first step only for melt history

**Path 1 and 2 - Extruded Pellet Sample Evaluation**

Property	Method	APR Guidance Preferred values	Additional Guidance
<u>Required values</u>			
Screen Pack Pressure Build	Practice O-P-06	End pressure no greater than 25% over starting pressure value	
Melt Flow Rate	ASTM – D1238	< 0.75 g/10minutes delta to the control	
Density	ASTM – D792 or ASTM 1505	Lower limit of test material with 50% innovation shall be no less than 0.941 g/cm <sup>3</sup>	Control no less than 0.941 g/cm <sup>3</sup>
Ash	ASTM – D5630		Perform if density is >0.98. Record and Report
Volatiles/Moisture	ASTM – D6980	< 0.5%	
DSC	ASTM – D3418	Primary Peak not to exceed 150C	Record primary and secondary peaks temp and J/g. Calculate the J/g delta from primary peak to secondary peak if present.
FTIR	ASTM – D7399	< 5% PP Content in test sample B (up to 10% allowable in innovation)	
Pellet Irregularity	Porosity, roughness, grainy, gloss etc..		Record, Report, and Photograph
Extrusion Process Irregularity	Unusual sticking, fumes, odor or build-up occurring at the feed throat or die exit of the extruder		Record and Report




**Path 1 and 2 – ASTM Part Evaluation**


<b><u>Property</u></b>	<b><u>Method</u></b>	<b><u>APR Guidance Preferred values</u></b>	<b><u>Additional Guidance</u></b>
<b><u>Required values</u></b>			
Melt Flow Rate	ASTM – D1238	< 0.75 g/10 minutes delta to the control	
Tensile Strength at Yield	ASTM – D638	No more than a 25% delta increase or decrease, control to test samples.	
Elongation at Break	ASTM – D638	No more than a 50% delta decrease, control to test sample, with a minimum value of 200%	
Notched Izod	ASTM – D256	Control and test samples should have the same break type or show greater ductility for test sample.	Record and report break type (no break, partial, hinge, complete) and values for the control and test.
Flexural Modulus	ASTM – D790	No more than a 25% delta decrease, control to test samples.	

<b>Property</b>	<b>Method</b>	<b>APR Guidance Preferred values</b>	<b>Additional Guidance</b>
<b><u>Optional value for Critical Guidance; Required for Applications Guidance and Bottle to Bottle Testing</u></b>			
ESCR	ASTM D1693		Record and Report – Preferred not to exceed 25% failures to the control for max. time reached.

### Path 1: Flow Diagram for HDPE Rigid Containers incorporating innovation



## Path 2: Flow Diagram for HDPE Rigid Resin incorporating innovations



## DOCUMENT VERSION HISTORY

<b>Version</b>	<b>Publication Date</b>	<b>Revision notes</b>
1	December 5, 2019	Made minor clarifying changes; approved by OTC on 10/2/19
2	July 8, 2020	Test and specification changes, Approved by OTC on 6/4/2020
3	June 3, 2021	Added language clarifying need for pre-requisite testing
4	August 17, 2021	Added expanded disclaimer language