

# The APR Design® Guide for Plastics Recyclability

## Supplemental Guidance

The following supplemental information is intended to be used alongside the Circular Packaging Assessment Tool. The information within is consistent with the [APR Design® Guide for Plastics Recyclability](#).

## Melt Flow Rate Calculation for HDPE blends

### Document Code – APR-RES -MFR-01

### Publication or Revision Date: 03/04/2024

#### Introduction – Scope, Significance and Use

For HDPE, LLDPE, and LDPE closures attached to HDPE containers the melt index (MI) of the closure and base resin blend needs to be less than 4.00 g/10 min to be considered APR Preferred. The MI of the blend can be measured experimentally using ASTM D1238. Alternatively, the Melt Flow Rate (MFR) of the closure and base resin blend can be calculated in lieu of laboratory testing.

**Disclaimer:** This document has been prepared by the Association of Plastic Recyclers as a service to the plastic industry to promote the most efficient use of the nation's plastic recycling infrastructure and to enhance the quality and quantity of recycled postconsumer plastic. The information in this document is offered without warranty of any kind, either expressed or implied, including WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, which are expressly disclaimed. APR and its members accept no responsibility for any harm or damages arising from the use of or reliance upon this information by any party. Participation in the Recognition Program is purely voluntary and does not guarantee compliance with any U.S. law or regulation or that a package or plastic article incorporating the innovation is recyclable or will be recycled.

## Calculation

APR Guidance given in the Critical Guidance method [HDPE-CG-01](#) is that the MFR of a 50/50 blend of control resin with an innovation should be less than 0.75 units greater than the control alone. The following calculation is offered and can be employed as an alternative to laboratory testing to determine the MFR of a blend of two different polyethylene resins:

$$\log(MFR_{blend}) = \sum w_i \log(MFR_i)$$

Using the lowest MFR control choice in the [O-P-01](#) of 0.25 g/10 min MFR and targeting 1.00 g/10 min (0.25 + 0.75 = 1.00 g/10 min) as the maximum MFR of the blend of closures and container base resin, one solves to determine the MFR for the blend of closures with base resin:

$$\log(MFR_{blend}) = 0.5 \log(4.00) \text{ (Closure + base resin blend)} + 0.5 \log(0.25) \text{ (Control)} = 0.00$$

$$MFR_{blend} = 1.00 \text{ (< } 0.75 + 0.25 \text{ per CG criteria)}$$

The table below gives some illustrative closure/container blends that do not exceed the < 4.00 g/10 min limit.

Cap (wt%)	Cap MFR (190/2.16)	Bottle (wt%)	Bottle MFR (190/2.16)	Blend Final MFR (<4.0 g/10 min)
0.10	15	0.90	0.25	0.38
0.20	20	0.80	0.70	1.37
0.30	30	0.70	0.35	1.33

### . Document Version History

Version	Publication Date	Revision notes
1	3/04/2024	Initial publications